

Makrolon® UV

Solid polycarbonate sheet



Your benefits:

- excellent weathering resistance
- extreme impact strength
- good fire rating
- thermoformable

Makrolon® UV sheets are made from clear-transparent polycarbonate sheets with UV protection on both sides. They are the perfect choice for a long service life owing to their good weathering resistance. These attributes are backed up by our 10-year guarantee on weathering resistance and a 10-year guarantee on retaining their mechanical properties.

Applications:

Makrolon® UV is ideal for outdoor applications:

- covered walkways and bus shelters
- barrel vaults and skylights (also thermoformed)

Available sizes:

Makrolon® UV is available in thicknesses of 2 – 15 mm and in the following sizes; other sizes, colors and sheet thicknesses on request.

Colors:

clear 2099
white 2130
white 2150
bronze 2850
grey 2760
blue 2550
green 2650

Sizes (Standard):

2,050 x 1,250 mm
3,050 x 2,050 mm
6,110 x 2,050 mm

	Test Conditions	Typical values ⁽¹⁾	Unit	Standard
PHYSICAL				
Density		1200	kg/m ³	ISO 1183-1
Water absorption saturation	water at 23 °C	0.30	%	ISO 62
Water absorption equilibrium	23 °C, 50% relative humidity	0.12	%	ISO 62
Refractive index	Procedure A	1.587	–	ISO 489
MECHANICAL				
Tensile modulus	1 mm/min	2350	MPa	ISO 527-1,-2
Yield stress	50 mm/min	> 60	MPa	ISO 527-1,-2
Yield strain	50 mm/min	6	%	ISO 527-1,-2
Nominal strain at break	50 mm/min	> 50	%	ISO 527-1,-2
Flexural modulus	2 mm/min	2350	MPa	ISO 178
Flexural strength	2 mm/min	90	MPa	ISO 178
Charpy impact strength	23 °C, unnotched	non-break	kJ/m ²	ISO 179-1eU
Charpy impact strength	23 °C, 3 mm, notched	80P	kJ/m ²	ISO 179-1eA
Izod impact strength	23 °C, 3.2 mm, notched	90P	kJ/m ²	ISO 180-A
THERMAL				
Vicat softening temperature	50 N, 50°C/h	148	°C	ISO 306
Thermal conductivity	23°C	0.20	W/(m.K)	ISO 8302
Coefficient of linear thermal expansion	23 to 55°C	0.65	10 ⁻⁴ /K	ISO 11359-1, -2
Temperature of deflection under load	1.80 Mpa	128	°C	ISO 75-1, -2
Temperature of deflection under load	0.45 Mpa	140	°C	ISO 75-1, -2
ELECTRICAL				
Electrical strength	1 mm	34	kV/mm	IEC 60243-1
Volume resistivity		1E14	Ohm.m	IEC 60093
Surface resistivity		1E16	Ohm	IEC 60093
Relative permittivity	100 Hz	3.1	–	IEC 60250
Relative permittivity	1 MHz	3.0	–	IEC 60250
Dissipation factor	100 Hz	5	10 ⁻⁴	IEC 60250
Dissipation factor	1 MHz	95	10 ⁻⁴	IEC 60250

⁽¹⁾ These values are measured on injection molded samples, and are not intended for specification purposes.

Product Liability Clause: This information and our technical advice – whether verbal, in writing or by way of trials – are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to verify the information currently provided – especially that contained in our safety data and technical information sheets – and to test products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with the current version of our General Conditions of Sale and Delivery.

Makrolon® UV

Solid polycarbonate sheet



Bayer MaterialScience S-Line, the standard product line, represents a range of certified quality products which offer the reliable solution for most applications.

Light Transmission: Test Method according to DIN 5036 - The stated thicknesses are not all available as standard. Please ask us for more information. The stated values are typical values only.

Light transmission in %	2	3	4	5	6	8	10	12	15
Makrolon® UV clear 2099	88	87	87	86	85	84	82	81	79
Makrolon® UV white 2130	40	30	23	18	13				
Makrolon® UV white 2150	60	50	40	33	28	20			
Makrolon® UV bronze 2850	63	50	50	50	50	50	42	36	
Makrolon® UV grey 2760		62	55	49	43	34	26		
Makrolon® UV green 2650		77	73	71	68	62	60	56	
Makrolon® UV blue 2550		61	55	51	46	40			

Fire Rating (*): Oxygen index (LOI) ISO 4589-2 Method A: 28%

Country	Standard	Rating	Thickness	Color
Germany	DIN 4102 DIN 5510-2 DIN 5510-2	B2 S3 SR2 ST2 S3 SR2 ST2	0.75 – 15 mm 4 mm 4 mm	all colors white 2130 white 2150
UK	BS 476 Part 7 BS 476 Part 7	Class 1Y Class 1Y	2,3,4,6 & 12 mm 5 mm	clear 2099 white 2130
France	NF P 92-501&505 NF F 16-101&102	M2 M2 F2 F2	2 – 15 mm 2 – 12 mm 2 – 15 mm 2 – 12 mm	clear 2099 bronze 2850 clear 2099 bronze 2850
Europe	EN 13501-1	B s1 d0 B s1 d0 B s2 d0	1 – 6 mm 1 – 3 mm 1 – 6 mm	clear 2099 white 2150 all colors except white 2150
USA	UL94	V2 HB V0	0.75 – 1.4 mm ≥ 1.5 mm ≥ 10 mm	all colors all colors clear 2099


Glow wire flammability index, IEC 60695-2-12, in °C (*):

	2	3	4	5	6
Makrolon® UV clear 2099	800		960		960
Makrolon® UV bronze 2850		960	960		
Makrolon® UV white 2130	960	960	960		
Makrolon® UV white 2150		960	960	960	960

(*) Fire certificates could be limited in time and scope, always check if the mentioned certificate is valid for the purchased Polycarbonate sheet type at the date of delivery. Polycarbonate sheets may change their fire behavior due to ageing and weathering. The indicated fire rating was tested on new / unweathered Product in accordance with the indicated fire classification standards.

Weathering Resistance: Makrolon® UV sheets show excellent weathering resistance, which guarantees their impact strength even after many years. Since their introduction in 1989, the sheets have been examined in an intensive test program, including a real-time outdoor exposure test in a southern European climate (Bandal). The sheets are provided with a 10-year warranty on unbreakability and on optical properties.

Permanent Service Temperature: The permanent service temperature without load is approx. 120 °C.



Bayer MaterialScience

Bayer MaterialScience GmbH
Otto-Hesse-Straße 19/T9, 64293 Darmstadt, Germany
Tel. +49 6151 13 03-0
Fax +49 6151 13 03-500

www.bayersheeteurope.com